

TECHNICAL DATA SHEET

TILESTIX – INTERO GRIP+

PHYSICAL PROPERTIES ARE AT 25° C

PHYSICAL PROPERTIES	
Mixing Ratio by weight	0.24 – 0.26
Mixed Density, kg/liter	1.60 – 1.80
Open Time, minutes (IS 15477: 2019)	Approx. 20
Adjustability, minutes (IS 15477: 2019)	Approx. 20
Pot Life, hours	2
Setting Time, hours	24
Time to Heavy Traffic, hours	24
Adhesive Thickness, mm	3 - 12
Application Temperature (Substrate and Materials), °C	5 - 35

PROPERTIES AS PER IS 15477: 2019 (TYPE 1T)

TESTING PROPERTIES	REQUIREMENT	TEST RESULTS
1. Tensile Adhesion Strength		
a. Dry Condition, N/mm ²	Minimum 0.5	>0.8
2. Shear Adhesion Strength		
b. Dry Condition, N/mm ²	Minimum 1.0	>1.10
3. Slip Resistance, mm	≤ 0.5	<0.3

PROPERTIES AS PER EN 12004: 2017 (C1T)

TESTING PROPERTIES	REQUIREMENT	TEST RESULTS
1. Open Time @ 20 minutes, N/mm ²	≥ 0.5	>0.6
2. Slip Resistance, mm	≤ 0.5	<0.3
3. Tensile Adhesion Strength		
a. Initial, N/mm ²	≥ 0.5	>0.8
b. After Water Immersion, N/mm ²	≥ 0.5	>0.7
c. After Heat Aging, N/mm ²	≥ 0.5	>0.8
d. After Freeze-Thaw Cycles, N/mm ²	≥ 0.5	>0.7

NOTE

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.